





ORAFOL's Worldwide Locations







ORACAL® Safety Series


These are transparent safety window films with 100 micron (single layered), 200 micron and 375 micron (double layered) thickness options and externally applied versions (Safety Exterior 100 - Safety Exterior 200). These safety films prevent impacted glass from being scattered, which reduces the risk of damage. They are suitable for use in buildings, glass facades, and motor vehicles.



• Expected Service Life: 10 Years / 5 Years (Exterior)

| | ORACAL® SAFETY 100 Micron | ORACAL® SAFETY 200 Micron | ORACAL® SAFETY 375 Micron | ORACAL® SAFETY Ext 100 Micron | ORACAL® SAFETY Ext 200 Micron |
|--------------------------------|---------------------------------|---------------------------------|---------------------------------|-------------------------------------|-------------------------------------|
| TSER** | 16.8% | 16.4% | 17.6% | 16.8% | 16.4% |
| UV Rejection | 99% | 99% | 99% | 99% | 99% |
| IR Rejection | 10% | 10% | 11% | 10% | 10% |
| Visible Light Reflected | 8% | 9.5% | 9.5% | 8% | 9.5% |
| Visible Light Transmitted | 88.9% | 88% | 86.9% | 88.9% | 88% |
| Solar Energy Absorbed | 9% | 10.8% | 12.3% | 9% | 10.8% |
| Solar Energy Reflected | 7% | 8.5% | 8.5% | 7% | 8.5% |
| Solar Energy Transmitted | 84% | 80.7% | 80.0% | 84% | 80.7% |
| Elongation at Break | 160% | 191% | 183% | 160% | 191% |
| Tensile Strength (N/10mm) | 151 | 297 | 459 | 151 | 297 |
| 180° Peeling Strength (N/10mm) | 4.5 | 2.8 | 1.1 | 4.5 | 2.8 |

^{**} Total Solar Energy Rejected





ORACAL® CA Series

These single layered automotive window films have an ideal thickness and are available in different tone options. While providing a good heat blocking performance, the color does not fade and the films are non-reflective.

- 38 micron
- Expected Service Life: 7 Years

| | ORACAL® CA'05 | ORACAL® CA'15 | ORACAL® CA'20 | ORACAL® CA'35 | ORACAL® CA'50 |
|-------------------------------------|------------------|------------------|------------------|------------------|------------------|
| TSER** | 50% | 48.6% | 45.5% | 41.2% | 35.5% |
| UV Rejection | 99% | 99% | 99% | 99% | 99% |
| IR Rejection | 31% | 31% | 31% | 31% | 30% |
| Solar Energy Absorbed | 60% | 57.9% | 54% | 47.8% | 39.6% |
| Solar Energy Reflected | 5.7% | 5.8% | 5.8% | 6.1% | 6.4% |
| Solar Energy Transmitted | 34.3% | 36.3% | 40.2% | 46.1% | 54% |
| Visible Light Reflected (ext) | 5.1% | 5.1% | 5% | 5.3% | 6.1% |
| Visible Light Reflected (int) | 4.8% | 5% | 5.2% | 5.5% | 6.2% |
| Visible Light Transmitted | 5.5% | 11% | 20.5% | 31.3% | 48% |

^{**} Total Solar Energy Rejected






ORACAL® Basic Series

These double layered auto glass films have an ideal thickness and are available in different tone options. The color of these films provides a natural look from inside. Additionally, the ORACAL® Basic Series offers a higher heat blocking performance than standard window films. ORACAL® Basic window films are easy to apply when the right methods and equipment are used.

- 38 micron
- Expected Service Life: 5 Years

| | ORACAL® Basic'05 | ORACAL® Basic'15 | ORACAL® Basic'20 | ORACAL® Basic'35 | ORACAL® Basic'50 |
|-------------------------------------|---------------------|---------------------|---------------------|---------------------|---------------------|
| TSER** | 54% | 52% | 50.6% | 46.5% | 42% |
| UV Rejection | 99% | 99% | 99% | 99% | 99% |
| IR Rejection | 37% | 37% | 37% | 37% | 37% |
| Solar Energy Absorbed | 62.4% | 59.7% | 57.2% | 50.9% | 44.3% |
| Solar Energy Reflected | 7.9% | 7.9% | 8.4% | 8.9% | 9.3% |
| Solar Energy Transmitted | 29.7% | 32.4% | 34.4% | 40.2% | 46.4% |
| Visible Light Reflected (ext) | 6.8% | 7.2% | 7.6% | 7.5% | 8.1% |
| Visible Light Reflected (int) | 4.8% | 4.9% | 5.3% | 5.9% | 7.3% |
| Visible Light Transmitted | 5.3% | 10.8% | 16.8% | 26.9% | 40.5% |

^{**} Total Solar Energy Rejected





ORACAL® NT Advanced Series

These are double-layered, nano-technological / carbon automotive window films with ideal thickness and different tone options. These series has a structure that prevents heat at highlevels. ORACAL® NT Advanced Series films are produced with advanced technology. These films provide ease of application when right methods and equipment are used.

- 38 micron
- Expected Service Life: 7 Years

| | ORACAL® NT Advanced'05 | ORACAL® NT Advanced'20 | ORACAL® NT Advanced'30 | ORACAL® NT Advanced'50 |
|-------------------------------|---------------------------|---------------------------|---------------------------|---------------------------|
| TSER** | 64.66% | 64.66% 59.21% | | 49.48% |
| UV Rejection | 99% | 99% | 99% | 99% |
| IR Rejection | 74.4% | 64.2% | 64.1% | 62.3% |
| Solar Energy Absorbed | 72.49% | 63.38% | 58.51% | 48.75% |
| Solar Energy Reflected | 11.08% | 12.39% | 12.61% | 13.45% |
| Solar EnergyTransmitted | 16.42% | 24.25% | 28.87% | 37.80% |
| Visible LightReflected (ext) | 6.19% | 7.42% | 7.99% | 9.48% |
| Visible Light Reflected (int) | 6.19% | 7.42% | 7.99% | 9.48% |
| Visible Light Transmitted | 6.3% | 16.8% | 29.3% | 46.02% |

^{**} Total Solar Energy Rejected





ORACAL® Windshield Film WS Series

This is a double-layered, nano-technology windshield film with ideal thickness, applied interiorly. The heat blocking performance of this product is higher than standard window films. These films are ideal for car windshield with the high level of clarity and light transmission in order not to hinder vision.

- 38 micron
- Expected Service Life: 7 Years

ORACAL® Windshield Film WS'70 Visible Light Transmitted Visible Light Solar Energy Transmitted Solar Energy Absorbed IR Rejection TSER** Solar Energy UV Rejection Reflected Reflected (int) 75.2% 35.72% 14.24% 50.03% 86.7% 51.22% 8.06% 99%



^{**} Total Solar Energy Rejected



ORACAL® Commercial S

These are silver/metallized building window films that are double layered, in ideal thickness, and available in different tone options. Using ORACAL® Commercial S Series in vehicles is not recommended because they are highly reflective. These films can be easily applied when the right methods and equipment are used.

- 50 micron
- Expected Service Life: 7 Years

| | ORACAL® Commercial S'00 | ORACAL® Commercial S'05 | ORACAL® Commercial S'20 | ORACAL® Commercial S'30 | ORACAL® Commercial S'50 | ORACAL® Commercial S'60 |
|-------------------------------------|-------------------------------|-------------------------------|-------------------------------|-------------------------------|-------------------------------|-------------------------------|
| TSER** | 93.6% | 88.5% | 74.7% | 61.2% | 39.9% | 33.5% |
| UV Rejection | 99% | 99% | 99% | 99% | 99% | 99% |
| IR Rejection | 99.4% | 94% | 82% | 71% | 48% | 39% |
| Solar Energy Absorbed | 14.6% | 29.9% | 26.9% | 29% | 31.3% | 29.7% |
| Solar Energy Reflected | 85% | 65.3% | 55.9% | 43.3% | 23.5% | 15.8% |
| Solar Energy Transmitted | 0.4% | 4.8% | 17.2% | 27.7% | 45.2% | 54.5% |
| Visible Light Reflected (ext) | 83.6% | 73.6% | 52.3% | 34.2% | 16.8% | 12.4% |
| Visible Light Reflected (int) | 87.7% | 77.7% | 56.7% | 38.2% | 20.3% | 14.9% |
| Visible Light Transmitted | 2.3% | 5.8% | 21.8% | 38% | 52.8% | 64.2% |

^{**} Total Solar Energy Rejected





ORACAL® Commercial S Plus Series

ORACAL® Commercial S Plus Window Films are developed for interior installations on architectural glass. These sputter films are provided in different tone options. ORACAL® Commercial S Plus Series provides an outstanding performance for solar heat rejection as well as a new appearance on buildings.

- 50 micron
- Expected Service Life: 7 Years

ORACAL® Commercial S Plus'35

| Visible Light Transmitted | Visible Light Reflected (int) | Visible Light Reflected (ext) | Solar Energy Transmitted | Solar Energy Reflected | Solar Energy Absorbed | IR Rejection | UV Rejection | TSER** |
|------------------------------|-------------------------------------|-------------------------------------|-----------------------------|---------------------------|--------------------------|-----------------|-----------------|--------|
| 37.6% | 52.1% | 50% | 24.5% | 52.3% | 23.2% | 85% | 99% | 70.3% |

ORACAL® Commercial S Plus'50

| Visible Light Transmitted | Visible Light Reflected (int) | Visible Light Reflected (ext) | Solar Energy Transmitted | Solar Energy Reflected | Solar Energy Absorbed | IR Rejection | UV Rejection | TSER** |
|------------------------------|-------------------------------------|-------------------------------------|-----------------------------|---------------------------|--------------------------|-----------------|-----------------|--------|
| 52% | 35.2% | 33.6% | 34.5% | 41.9% | 23.6% | 75% | 99% | 60.1% |

^{**} Total Solar Energy Rejected





ORAFOL TURKEY Akçaburgaz Mh. 9. Cd. 117. Sk. No:5 Kıraç / Esenyurt, 34522 İstanbul, Turkey

Tel: +90 212 671 26 83 / info@orafol.com.tr

Find out more about our products at: www.orafol.com.tr



