


ORALITE® 6710

Engineer Prismatic Grade

ORALITE® 6710 Engineer Prismatic Grade is a CE-certified reflective film with excellent reflection properties and high weather resistance. Specially developed for bonding on smooth metal surfaces such as aluminum and galvanized steel.

Reflective Properties

Cell structure:



Reflective Technology: Prismatic , Reflectivity classes: RA1, Reflective film structure: C

Areas of Application

- Traffic signs
- Construction sites
- Traffic & transportation
- Advertising & signage

Colours

ORALITE® 6710 is available in the following colors: White (color code 010), Yellow (color code 020), Orange (color code 035), Red (color code 030), Blue (color code 050), Green (color code 060), Brown (color code 080)

Total thickness

- 0.28mm (Standard colours, average value, without protective liner)
- 0.37mm (fluorescent colours, average value, without protective paper)

Front material

Acrylic film

Liner

One-sided silicon-coated PP film, 0.06 mm

Adhesive

Solvent-polyacrylate

ORALITE® 6710

Engineer Prismatic Grade

Certificates

- 2018-09-18 Orafol 6710 0913-CPR-2016-11-1.pdf [\(Download\)](#)
- 2021-07-29 Orafol 6710 0913-CPR-2016-11 Anlage.pdf [\(Download\)](#)
- 2018-09-18 Orafol 6710 0913-CPR-2016-11 Anlage-1.pdf [\(Download\)](#)
- DoP6710.001.20220208-DE.pdf [\(Download\)](#)
- 2018-09-18 Orafol 6710 0913-CPR-2016-11 UK-1.PDF [\(Download\)](#)
- 2021-07-29 Orafol 6710 0913-CPR-2016-11 Anlage UK.pdf [\(Download\)](#)
- DoP6710.001.20221108-EN.pdf [\(Download\)](#)
- 2018-09-18 Orafol 6710 0913-CPR-2016-11 Anlage UK.PDF [\(Download\)](#)
- 2018-09-18 Orafol 6710 0913-CPR-2016-11 Anlage UK.PDF [\(Download\)](#)
- 2018-09-18 Orafol 6710 0913-CPR-2016-11 Anlage UK.PDF [\(Download\)](#)
- 2018-09-18 Orafol 6710 0913-CPR-2016-11 Anlage UK.PDF [\(Download\)](#)
- 1519~1 6710 approval.pdf [\(Download\)](#)
- 6710 EGP SABS report short.pdf [\(Download\)](#)
- 6710-030 RED- SABS test report Final.pdf [\(Download\)](#)

Technical properties

RESISTANCE

Resistance to cleaning agents	No change	adhered on aluminium 8 h in detergent solution (0.5 % household cleaner) at room temperature and 65 °C
Durability	7 Year(s)	unprinted, with professional processing, with vertical outdoor weathering, central European normal climate
Shelf Life	1 Year(s)	in original packaging, at 20 °C and 50 % relative humidity
Temperature resistance	Minimum temperature -40 °C Maximum temperature 80 °C	adhered on aluminium

ADHESIVE PROPERTIES

Adhesive power	15 N/25 mm	after 24 h, on stainless steel Average value, FINAT TM 1
----------------	------------	--

ORALITE® 6710

Engineer Prismatic Grade

PROCESSING

Recommended printing procedure	Screen printing, Digital print with UV-curing inks
Suitable substrate	Metals, Aluminium, Galvanised sheet steel
Application temperature	Minimum temperature 10 °C

PRODUCT NOTE

The substrate to be bonded must be free of dust, grease or other contamination, which can affect the adhesiveness of the material. The adhesive is designed for metallic substrates. For other application areas the user is responsible for testing and assessing whether the product is suitable and whether risks may arise from its use. ORALITE® 6710 in white can be printed in screen printing with ORALITE® 5018 Screen Printing Ink. Clear varnish is not required. Printing via UV digital printing is also possible. The ORALITE® UV Traffic Sign Printer in combination with the UV digital print inks ORALITE® 5019 developed specifically for this purpose as well as the laminate ORALITE® 5062 Transparent Film is approved for the application. The printed or laminated material fulfils the specifications for colour location and reflection value of this colour if the ORAFOL processing instructions are observed. For detailed information please refer to the processing instructions No. 4.3. published by ORAFOL or contact the responsible employee of the ORAFOL Reflective Solutions Division. All ORALITE® products have been manufactured in a production process certified in accordance with ISO 9001:2015. The batch can be traced at any time by means of the roll number.

IMPORTANT NOTES

Observe the relevant national specifications when using the ORALITE® films. ORAFOL recommends that you obtain the current specifications from your local authority and ensure that the product complies with them. For further information, please contact ORAFOL directly. All ORALITE® products are subject to thorough quality control during the entire manufacturing process. It is ensured that they are of merchantable quality and free from manufacturing defects. The information published on the ORALITE® products is based on research results which the company considers to be reliable, but which do not constitute a guarantee. In view of the wide range of applications of ORALITE® products and the continuous development of new applications, the buyer should carefully weigh up the suitability and performance of the product for the respective purpose and they bear all risks in connection with such use. All specifications may be changed without advance notice. Any warranty is excluded for applications which are not listed in the Technical Data sheet or which are not performed in accordance with the processing guidelines set out by ORAFOL. The durability of the shields depends on a multitude of factors, such as for example the selection and preparation of the substrate, compliance with the recommended processing guidelines, the geographical application area, the weather conditions as well as the maintenance of the product and the finished shield. ORAFOL does not accept any liability for defects which can be traced back to an unsuitable substrate or inadequate surface preparation. You can find comprehensive information in the warranty document under www.orafol.com. ORALITE® is a trademark of ORAFOL Europe GmbH.