

ORACAL® 1640

Print Vinyl

Short description

Soft PVC film available in transparent and white. Surface glossy and matt.

Front material

Soft PVC Film, 0.1 mm

Liner

One-sided siliconized kraft paper, 137 g/m²

Adhesive

Polyacrylate permanent, Transparent, 19 mm

Technical properties

RESISTANCE

Durability	with vertical outdoor exposure, normal Central European climate	
	3 Year(s)	
Shelf Life	2 Year(s)	in original packaging, at 20 °C and 50% relative humidity
Maximum shrinkage	Maximum shrinkage along 0.4 mm Maximum shrinkage across 0 mm	bonded to steel FINAT TM 14 FINAT TM 14
Elongation at break	Minimum elongation at break along 130 % Minimum elongation at break across 150 %	DIN EN ISO 527
Tensile strength	Minimum tensile strength along 19 N/mm ² Minimum tensile strength across 19 N/mm ²	DIN EN ISO 527
Temperature resistance	Minimum temperature -40 °C Maximum temperature 60 °C	Short-term exposure up to 80 °C

ADHESIVE PROPERTIES

Adhesive power	16 N/25 mm	after 24 h, on stainless steel FINAT TM 1
----------------	------------	---

ORACAL® 1640

Print Vinyl

PROCESSING

Application temperature	Minimum temperature 10 °C
-------------------------	---------------------------

Certificates

- 1640G 010 000 C-s2_d0 Mineralischer_Untergrund Klassifizierung nach DIN EN 13501-1.pdf [\(Download\)](#)
- 1640G 010 000 C-s2_d0 Mineralischer_Untergrund Klassifizierung nach DIN EN 13501-1.pdf [\(Download\)](#)
- 1640G 010 000 C-s2_d0 Mineralischer_Untergrund Klassifizierung nach DIN EN 13501-1.pdf [\(Download\)](#)
- 1640G 010 000 C-s2_d0 Mineralischer_Untergrund Klassifizierung nach DIN EN 13501-1.pdf [\(Download\)](#)
- 1640G 010 000 C-s2_d0 Mineralischer_Untergrund Klassifizierung nach DIN EN 13501-1.pdf [\(Download\)](#)
- 1640G 010 000 C-s2_d0 Mineralischer_Untergrund Klassifizierung nach DIN EN 13501-1.pdf [\(Download\)](#)

PRODUCT NOTE

Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any other contamination that could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material.

IMPORTANT NOTES

All ORACAL® products are subject to careful quality control throughout the manufacturing process. It is guaranteed that the products are delivered in merchantable quality and free of manufacturing defects. The traceability of our goods in accordance with ISO 9001 is ensured by means of the roll number. The information published on ORACAL® products is based on research results which the company believes to be reliable, but which do not constitute a guarantee. Because of the wide variety of uses of ORACAL® products and the continuing development of new applications, it is the responsibility of the purchaser to carefully evaluate the suitability and performance of the product for its intended use. Furthermore, the processing instructions issued by ORAFOL must be observed. The purchaser bears all risks arising from the use of these products. All information is subject to change without notice. ORACAL® is a registered trademark of ORAFOL Europe GmbH.