

# ORACAL® 1640HT

## Print Vinyl

### Short description

Very supple soft PVC film, surface glossy and matt.

### Front material

Soft PVC Film, 0.1 mm

### Liner

One-sided siliconized kraft paper, 137 g/m<sup>2</sup>

### Adhesive

Polyacrylate permanent, Transparent, 0.023 mm

### Technical properties

#### RESISTANCE

|                        |                                                                 |                                                           |
|------------------------|-----------------------------------------------------------------|-----------------------------------------------------------|
| Durability             | with vertical outdoor exposure, normal Central European climate |                                                           |
|                        | 3 Year(s)                                                       |                                                           |
| Shelf Life             | 2 Year(s)                                                       | in original packaging, at 20 °C and 50% relative humidity |
| Maximum shrinkage      | Maximum shrinkage along 0.4 mm                                  | bonded to steel   FINAT TM 14                             |
|                        | Maximum shrinkage across 0 mm                                   | FINAT TM 14                                               |
| Elongation at break    | Minimum elongation at break along 130 %                         | DIN EN ISO 527                                            |
|                        | Minimum elongation at break across 150 %                        |                                                           |
| Tensile strength       | Minimum tensile strength along 19 N/mm <sup>2</sup>             | DIN EN ISO 527                                            |
|                        | Minimum tensile strength across 19 N/mm <sup>2</sup>            |                                                           |
| Temperature resistance | Minimum temperature -40 °C                                      | Short-term exposure up to 80 °C                           |
|                        | Maximum temperature 60 °C                                       |                                                           |

# ORACAL® 1640HT

## Print Vinyl

### ADHESIVE PROPERTIES

|                |            |                                                            |
|----------------|------------|------------------------------------------------------------|
| Hi-tack        | Yes        |                                                            |
| Adhesive power | 22 N/25 mm | after 24 h, on stainless steel   Average value, FINAT TM 1 |

### PROCESSING

|                         |                           |
|-------------------------|---------------------------|
| Application temperature | Minimum temperature 10 °C |
|-------------------------|---------------------------|

### PRODUCT NOTE

Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any other contamination that could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material.

### IMPORTANT NOTES

All ORACAL® products are subject to careful quality control throughout the manufacturing process. It is guaranteed that the products are delivered in merchantable quality and free of manufacturing defects. The traceability of our goods in accordance with ISO 9001 is ensured by means of the roll number. The information published on ORACAL® products is based on research results which the company believes to be reliable, but which do not constitute a guarantee. Because of the wide variety of uses of ORACAL® products and the continuing development of new applications, it is the responsibility of the purchaser to carefully evaluate the suitability and performance of the product for its intended use. Furthermore, the processing instructions issued by ORAFOL must be observed. The purchaser bears all risks arising from the use of these products. All information is subject to change without notice. ORACAL® is a registered trademark of ORAFOL Europe GmbH.