

ORACAL® 8510

Etched Glass Cal

Short description

Special PVC film with polymer plasticisers for glass decoration. The reduced surface gloss of the film prevents unwanted reflections. Available in the colours silver and gold as well as in different surface structures.

Front material

Polymer PVC film, 0.08 mm

Liner

One-sided siliconized kraft paper, 137 g/m²

Adhesive

Solvent-polyacrylate, permanent, Transparent, 0.026 mm

Recommended transfer materials

ORATAPE® HT95 Application Tape, ORATAPE® LT52 Application Tape, ORATAPE® MT95 Application Tape, ORATAPE® LT95 Application Tape, ORATAPE® MT52 Application Tape, ORATAPE® MT72 Application Tape, ORATAPE® MT80P Application Tape

Technical properties

RESISTANCE

Durability	with vertical outdoor exposure, normal Central European climate 7 Year(s)	
Shelf Life	2 Year(s)	in original packaging, at 20 °C and 50% relative humidity
Resistance to solvents and chemicals	Oils, Greases, Fuels, Weak acids, Salts and alkalis, Isopropyl alcohol, Washing suds (0.5 % household cleaner)	At room temperature
Maximum shrinkage	Maximum shrinkage along 0.2 mm Maximum shrinkage across 0 mm	adhered on glass FINAT TM 14
Elongation at break	Minimum elongation at break along 130 % Minimum elongation at break across 150 %	DIN EN ISO 527

ORACAL® 8510

Etched Glass Cal

Tensile strength	Minimum tensile strength along 19 N/mm ² Minimum tensile strength across 19 N/mm ²	EN ISO 527
Temperature resistance	Minimum temperature -40 °C Maximum temperature 60 °C	bonded to acrylic glass, normal Central European climate

ADHESIVE PROPERTIES

Adhesive power	18 N/25 mm 16 N/25 mm	after 24 h, on stainless steel Average value, FINAT TM 1
----------------	--------------------------	--

PROCESSING

Application temperature	Minimum temperature 10 °C
Proposed application technology	Wet application

Certificates

- 8510 B-s1_d0 auf Glas Klassifizierung nach DIN EN 13501-1 de.pdf (Download)
- ORACAL_8510_-_Verklebung_auf_Brandschutzverglasung.pdf (Download)
- ORACAL_8510_-_Verklebung_auf_Brandschutzverglasung.pdf (Download)
- 8510 B-s1_d0 auf Glas Klassifizierung nach DIN EN 13501-1 en.pdf (Download)
- 8510 B-s1_d0 auf Glas Klassifizierung nach DIN EN 13501-1 en.pdf (Download)
- ORACAL_8510_-_Verklebung_auf_Brandschutzverglasung.pdf (Download)
- ORACAL_8510_-_Verklebung_auf_Brandschutzverglasung.pdf (Download)
- 8510 B-s1_d0 auf Glas Klassifizierung nach DIN EN 13501-1 en.pdf (Download)
- 8510 B-s1_d0 auf Glas Klassifizierung nach DIN EN 13501-1 en.pdf (Download)
- ORACAL_8510_-_Verklebung_auf_Brandschutzverglasung.pdf (Download)
- ORACAL_8510_-_Verklebung_auf_Brandschutzverglasung.pdf (Download)
- 8510 B-s1_d0 auf Glas Klassifizierung nach DIN EN 13501-1 en.pdf (Download)

ORACAL® 8510

Etched Glass Cal

PRODUCT NOTE

Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any other contamination that could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material.

IMPORTANT NOTES

All ORACAL® products are subject to careful quality control throughout the manufacturing process. It is guaranteed that the products are delivered in merchantable quality and free of manufacturing defects. The traceability of our goods in accordance with ISO 9001 is ensured by means of the roll number. The information published on ORACAL® products is based on research results which the company believes to be reliable, but which do not constitute a guarantee. Because of the wide variety of uses of ORACAL® products and the continuing development of new applications, it is the responsibility of the purchaser to carefully evaluate the suitability and performance of the product for its intended use. Furthermore, the processing instructions issued by ORAFOL must be observed. The purchaser bears all risks arising from the use of these products. All information is subject to change without notice. ORACAL® is a registered trademark of ORAFOL Europe GmbH.