

# ORACAL® 8800

## Translucent Premium Cast

### Short description

Cast translucent coloured film with excellent colour uniformity at incident and transmitted light. The silky-gloss surface texture of the film prevents unwanted reflections

### Front material

Cast PVC film, cast film, 0.05 mm

### Liner

Polyester film, siliconised on one side, 0.1 mm

### Adhesive

Solvent-polyacrylate permanent, Transparent, 0.03 mm

### Recommended transfer materials

ORATAPE® HT95 Application Tape, ORATAPE® LT52 Application Tape, ORATAPE® MT95 Application Tape, ORATAPE® LT95 Application Tape, ORATAPE® MT52 Application Tape, ORATAPE® MT72 Application Tape, ORATAPE® MT80P Application Tape

### Technical properties

#### RESISTANCE

|                   |                                                                 |                                                           |
|-------------------|-----------------------------------------------------------------|-----------------------------------------------------------|
| Durability        | with vertical outdoor exposure, normal Central European climate |                                                           |
|                   | 10 Year(s)                                                      | Black, white                                              |
|                   | 8 Year(s)                                                       | coloured                                                  |
|                   | 5 Year(s)                                                       | metallic                                                  |
| Shelf Life        | 2 Year(s)                                                       | in original packaging, at 20 °C and 50% relative humidity |
| Maximum shrinkage | Maximum shrinkage along 0.1 mm                                  | bonded to steel                                           |
|                   | Maximum shrinkage across 0.1 mm                                 |                                                           |

# ORACAL® 8800

## Translucent Premium Cast

|                        |                                                         |                                 |
|------------------------|---------------------------------------------------------|---------------------------------|
| Elongation at break    | Minimum elongation at break along 120 %                 | DIN EN ISO 527                  |
|                        | Minimum elongation at break across 120 %                |                                 |
| Tensile strength       | Minimum tensile strength along 21 N/mm <sup>2</sup>     | DIN EN ISO 527                  |
|                        | Minimum tensile strength across 21 N/mm <sup>2</sup>    |                                 |
| Temperature resistance | Minimum temperature -40 °C<br>Maximum temperature 60 °C | Short-term exposure up to 80 °C |

### ADHESIVE PROPERTIES

|                |            |                                                            |
|----------------|------------|------------------------------------------------------------|
| Adhesive power | 18 N/25 mm | adhered on glass, after 24 h   Average value, FINAT TM 1   |
|                | 16 N/25 mm | adhered on acrylic, after 24 h   Average value, FINAT TM 1 |

### PROCESSING

|                         |                           |
|-------------------------|---------------------------|
| Application temperature | Minimum temperature 10 °C |
|-------------------------|---------------------------|

### PRODUCT NOTE

Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any other contamination that could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material.

### IMPORTANT NOTES

All ORACAL® products are subject to careful quality control throughout the manufacturing process. It is guaranteed that the products are delivered in merchantable quality and free of manufacturing defects. The traceability of our goods in accordance with ISO 9001 is ensured by means of the roll number. The information published on ORACAL® products is based on research results which the company believes to be reliable, but which do not constitute a guarantee. Because of the wide variety of uses of ORACAL® products and the continuing development of new applications, it is the responsibility of the purchaser to carefully evaluate the suitability and performance of the product for its intended use. Furthermore, the processing instructions issued by ORAFOL must be observed. The purchaser bears all risks arising from the use of these products. All information is subject to change without notice. ORACAL® is a registered trademark of ORAFOL Europe GmbH.