

ORACAL® 961

Caravan Film Premium Cast

Short description

Moulded premium PVC film, with excellent adhesive properties on difficult substrates, in glossy white, black, silver grey, yolk yellow (further colours on request)

Front material

Cast PVC film, cast film, 0.055 mm

Liner

One-sided siliconized kraft paper, 137 g/m²

Adhesive

Solvent-polyacrylate permanent, Transparent, 0.04 mm

Technical properties

RESISTANCE

Durability	with vertical outdoor exposure, normal Central European climate	
	10 Year(s)	Black, white, applies for vertical outdoor weathering and central European normal climate
	8 Year(s)	coloured, applies for vertical outdoor weathering and central European normal climate
	6 Year(s)	Metallic: silver grey, applies for vertical outdoor weathering and central European normal climate
Shelf Life	2 Year(s)	in original packaging, at 20 °C and 50% relative humidity
Resistance to solvents and chemicals	Aliphatic solvents, Oils, Greases, Fuels, Weak acids, Salts and alkalis	At room temperature
Maximum shrinkage	Maximum shrinkage along 0.2 mm	bonded to steel FINAT TM 14
	Maximum shrinkage across 0.2 mm	bonded to steel FINAT TM 14

ORACAL® 961

Caravan Film Premium Cast

Elongation at break	Minimum elongation at break along 150 %	Metallic: 120%, DIN EN ISO 527
	Minimum elongation at break across 150 %	Metallic: 120%, DIN EN ISO 527
Tensile strength	Minimum tensile strength along 21 N/mm ²	DIN EN ISO 527
	Minimum tensile strength across 21 N/mm ²	
Seawater resistance	no change	after 100h/35°C adhered to aluminum, DIN EN ISO 9227
Temperature resistance	Minimum temperature -40 °C	Short-term exposure up to 80 °C
	Maximum temperature 60 °C	

ADHESIVE PROPERTIES

Adhesive power	30 N/25 mm	after 24 h, stainless steel FINAT TM 1
----------------	------------	--

PROCESSING

Application temperature	Minimum temperature 10 °C
-------------------------	---------------------------

PRODUCT NOTE

Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any other contamination that could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material.

IMPORTANT NOTES

All ORACAL® products are subject to careful quality control throughout the manufacturing process. It is guaranteed that the products are delivered in merchantable quality and free of manufacturing defects. The traceability of our goods in accordance with ISO 9001 is ensured by means of the roll number. The information published on ORACAL® products is based on research results which the company believes to be reliable, but which do not constitute a guarantee. Because of the wide variety of uses of ORACAL® products and the continuing development of new applications, it is the responsibility of the purchaser to carefully evaluate the suitability and performance of the product for its intended use. Furthermore, the processing instructions issued by ORAFOL must be observed. The purchaser bears all risks arising from the use of these products. All information is subject to change without notice. ORACAL® is a registered trademark of ORAFOL Europe GmbH.