

ORACAL®

Safety Window Film

Short description

PET window safety film with a one- or multi-layered structure* to protect against impact and glass breakage. The highly transparent Safety Window Films are available in different film thicknesses. The film is suitable for indoor installation in buildings, on glass facades and vehicles.

Front material

PET film, 0.1 mm

Liner

Polyester film, siliconised on one side

Adhesive

Solvent-polyacrylate permanent, Transparent

Technical properties

RESISTANCE

Durability	for indoor use, normal Central European climate	
	10 Year(s)	
Shelf Life	2 Year(s)	in original packaging, at 20 °C and 50% relative humidity
Temperature resistance	Minimum temperature -40 °C	
	Maximum temperature 100 °C	

ADHESIVE PROPERTIES

Adhesive power	4.5 N-10mm
----------------	------------

PROCESSING

Application temperature	Minimum temperature 10 °C
-------------------------	---------------------------

ORACAL®

Safety Window Film

Proposed application
technology

Wet application

SUN PROTECTION PROPERTIES

Glare reduction	1 %
IR rejection	10 %
Reflecting (visible light, indoors)	8 %
Solar energy absorption	9 %
Solar energy reflection	7 %
Solar energy transmission	84 %
Total solar energy rejection	16.8 %
Transmission (visible light)	88.9 %
UV rejection	99 %

PRODUCT NOTE

Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any other contamination that could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material.

IMPORTANT NOTES

All ORACAL® products are subject to careful quality control throughout the manufacturing process. It is guaranteed that the products are delivered in merchantable quality and free of manufacturing defects. The traceability of our goods in accordance with ISO 9001 is ensured by means of the roll number. The information published on ORACAL® products is based on research results which the company believes to be reliable, but which do not constitute a guarantee. Because of the wide variety of uses of ORACAL® products and the continuing development of new applications, it is the responsibility of the purchaser to carefully evaluate the suitability and performance of the product for its intended use. Furthermore, the processing instructions issued by ORAFOL must be observed. The purchaser bears all risks arising from the use of these products. All information is subject to change without notice. ORACAL® is a registered trademark of ORAFOL Europe GmbH.