

ORAGUARD® 252F

Laminating Film

Short description

Highly transparent, glossy, cast PVC high performance film with a highly effective UV protection.

Front material

Cast PVC film, cast film, 0.05 mm

Liner

PET film, single-side silicone coated, 0.075 mm

Adhesive

Solvent-polyacrylate permanent, Transparent, 0.028 mm

Technical properties

RESISTANCE

Durability	with vertical outdoor exposure, normal Central European climate	
	8 Year(s)	
Shelf Life	2 Year(s)	in original packaging, at 20 °C and 50% relative humidity
Resistance to solvents and chemicals	Weak acids, Salts and alkalis, Water, Isopropyl alcohol, Washing suds (0.5 % household cleaner)	At room temperature
Maximum shrinkage	Maximum shrinkage along 0.3 mm Maximum shrinkage across 0.3 mm	Short-term load, bonded to steel
Elongation at break	Minimum elongation at break along 120 % Minimum elongation at break across 120 %	DIN EN ISO 527, average value
Tensile strength	Minimum tensile strength along 19 N/mm ² Minimum tensile strength across 19 N/mm ²	DIN EN ISO 527

ORAGUARD® 252F

Laminating Film

Temperature resistance

Minimum temperature -40 °C
Maximum temperature 60 °C

Short-term exposure up to 80 °C

ADHESIVE PROPERTIES**Adhesive power**

12 N/25 mm

after 24 h, on stainless steel, average value | FINAT TM 1

PROCESSING**Application temperature**

Minimum temperature 10 °C

PRODUCT NOTE

Due to the diversity of prints and printing techniques, the user should test the suitability of ORAGUARD® laminating films for the specific print purpose, prior to use. Furthermore the application information published by ORAFOL must be followed.

IMPORTANT NOTES

All ORAGUARD® products are subject to careful quality control during the entire manufacturing process. It is guaranteed that the products are delivered in merchantable quality and free of manufacturing defects. The traceability of our goods in accordance with ISO 9001 is ensured by means of the roll number. The information published on ORAGUARD® products is based on research results which the company believes to be reliable, but which do not constitute a guarantee. Due to the wide variety of uses of ORAGUARD® products and the continuing development of new applications, it is the responsibility of the purchaser to carefully evaluate the suitability and performance of the product for its intended use. Furthermore, the processing instructions issued by ORAFOL must be observed. The purchaser bears all risks arising from the use of these products. All information is subject to change without notice.