

ORAGUARD® PPF2815GF

Paint Protection Film

Short description

Surface functionalised polyurethane film, highly transparent, glossy with excellent UV resistance and self-healing surface. The surface has a particularly high resistance to chemicals. The migration of dirt is prevented effectively in the film through the surface coating - meaning that the 2815GF is resistant to yellowing.

Front material

Polyurethane film, 0.16 mm

Liner

PET film, single-side silicone coated

Adhesive

Solvent-polyacrylate, permanent, Transparent, 0.04 mm

Technical properties

RESISTANCE

Ageing test	1000 Hour(s)	Xenon weathering according to EN ISO 4892
Durability	with vertical outdoor exposure, normal Central European climate 10 Year(s)	
Shelf Life	2 Year(s)	in original packaging, at 20 °C and 50% relative humidity
Resistance to solvents and chemicals	Water, Sulphuric acid (10 %), Hydrochloric acid (10 %), Bird droppings (pancreatin), Tree resin, Fuels, Motor oil, Isopropyl alcohol	Immersion for: 1 hour (water, acid), 30 min (pancreatin, tree resin), 10 min (isopropyl alcohol, fuel, engine oil), check after 24 h at RT
Maximum shrinkage	Maximum shrinkage along 0.2 mm Maximum shrinkage across 0.2 mm	Bonded to steel max.
Elongation at break	Minimum elongation at break along 300 % Minimum elongation at break across 300 %	DIN EN ISO 527

ORAGUARD® PPF2815GF

Paint Protection Film

Tensile strength	Minimum tensile strength along 29 N/mm ² Minimum tensile strength across 29 N/mm ²	DIN EN ISO 527
Stone chip resistance	Passed	To SAE J400 2.4L gravel
Temperature resistance	Minimum temperature -40 °C Maximum temperature 100 °C	

ADHESIVE PROPERTIES

Adhesive power	17 N/25 mm	after 24 h, on stainless steel, average value FINAT TM 1
----------------	------------	--

PROCESSING

Application temperature	Minimum temperature 10 °C	
Proposed application technology	Wet application	Wet application procedure with ORAFOL Application Gel

PRODUCT NOTE

Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any other contamination that could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. We recommend wet application of the film.

IMPORTANT NOTES

All ORAGUARD® products are subject to careful quality control during the entire manufacturing process. It is guaranteed that the products are delivered in merchantable quality and free of manufacturing defects. The traceability of our goods in accordance with ISO 9001 is ensured by means of the roll number. The information published on ORAGUARD® products is based on research results which the company believes to be reliable, but which do not constitute a guarantee. Due to the wide variety of uses of ORAGUARD® products and the continuing development of new applications, it is the responsibility of the purchaser to carefully evaluate the suitability and performance of the product for its intended use. Furthermore, the processing instructions issued by ORAFOL must be observed. The purchaser bears all risks arising from the use of these products. All information is subject to change without notice.