ORAJET® XP1902

Digital Printing Paper

Short description

Coated paper (120 g/m²) white, coated on one side with a special matt inkjet coating.

Front material

Coated paper, 0.1 mm

Liner

One-sided siliconized kraft paper, 85 g/m²

Adhesive

Polyacrylate, permanent, Grey, 0.023 mm

Recommended inks

Dye-Tinten, Pigment Tinte

Technical properties

RESISTANCE		
Durability	10 Year(s)	indoors
Shelf Life	1 Year(s)	in original packaging, at 20 °C and 50% relative humidity
Temperature resistance	Minimum temperature -40 °C Maximum temperature 60 °C	Short-term exposure up to 110 °C
ADHESIVE PROPERTIES		
Adhesive power	16 N/25 mm	after 24 h, on stainless steel | FINAT TM 1, average value
PROCESSING		
Recommended inks	Dye inks, Pigment ink	
Application temperature	Minimum temperature 10 °C	

ORAFOL Europe GmbH
Orafolstrasse 1
D-16515 Oranienburg
Germany

Tel: +49 (0)3301 864-0
graphic.solutions@orafol.de
www.orafol.com

ORAJET® XP1902

Digital Printing Paper

PRODUCT NOTE

After printing, the ink must be allowed to thoroughly dry, in order to avoid any issues when later combined with the laminate. Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of the selected lacquers and paints should be tested by the user, prior to the application of the material. Furthermore the application information published by ORAFOL must be considered.

IMPORTANT NOTES

All ORAJET® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORAJET® products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of ORAJET® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice ORAJET® is a registered trademark of ORAFOL Europe GmbH.

ORAFOL Europe GmbH
Orafolstrasse 1
D-16515 Oranienburg
Germany

Tel: +49 (0)3301 864-0
graphic.solutions@orafol.de
www.orafol.com