

ORAJET® 3268

Wall Art Digital

Short description

Extra-strong soft PVC film for indoor wallpaper decorations and advertising. Available in white with a matt finish.

Front material

Soft PVC Film, 0.15 mm

Liner

One-sided siliconized kraft paper, 137 g/m²

Adhesive

Polyacrylate, removable, Transparent, 0.018 mm

Recommends laminating films

ORAGUARD® 213

Technical properties

RESISTANCE

Durability	with vertical outdoor exposure, normal Central European climate	
	2 Year(s)	with vertical outdoor weathering, central European normal climate
Shelf Life	2 Year(s)	in original packaging, at 20 °C and 50% relative humidity
Maximum shrinkage	Maximum shrinkage along 0.4 mm Maximum shrinkage across 0 mm	
Elongation at break	Minimum elongation at break along 180 % Minimum elongation at break across 200 %	
Tensile strength	Minimum tensile strength along 30 N/mm ² Minimum tensile strength across 28 N/mm ²	DIN EN ISO 527
Temperature resistance	Minimum temperature -40 °C Maximum temperature 60 °C	Short-term exposure up to 80 °C

ORAJET® 3268

Wall Art Digital

ADHESIVE PROPERTIES

Adhesive power	6 N/25 mm	after 24 h, on stainless steel Average value, FINAT TM 1
----------------	-----------	--

PROCESSING

Application temperature	Minimum temperature 10 °C
-------------------------	---------------------------

Certificates

- 3268M-010 C-s2_d0 - Mineralischer_Untergrund - Klassifizierung nach DIN EN 13501-1.pdf (Download)
- 3268M-010 C-s2_d0 Mineralischer_Untergrund Klassifizierung nach DIN EN 13501-1 - en.pdf (Download)
- 3268M-010 C-s2_d0 Mineralischer_Untergrund Klassifizierung nach DIN EN 13501-1 - en.pdf (Download)
- 3268M-010 C-s2_d0 Mineralischer_Untergrund Klassifizierung nach DIN EN 13501-1 - en.pdf (Download)
- 3268M-010 C-s2_d0 Mineralischer_Untergrund Klassifizierung nach DIN EN 13501-1 - en.pdf (Download)
- 3268M-010 C-s2_d0 Mineralischer_Untergrund Klassifizierung nach DIN EN 13501-1 - en.pdf (Download)

PRODUCT NOTE

After printing, the ink must be allowed to thoroughly dry, in order to avoid any issues when later combined with the laminate. Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of the selected lacquers and paints should be tested by the user, prior to the application of the material. Furthermore the application information published by ORAFOL must be considered.

IMPORTANT NOTES

All ORAJET® products are subject to careful quality control throughout the manufacturing process. It is guaranteed that the products are delivered in merchantable quality and free of manufacturing defects. The traceability of our goods in accordance with ISO 9001 is ensured by means of the roll number. The information published on ORAJET® products is based on research results which the company believes to be reliable but does not constitute a guarantee. Because of the wide variety of uses of ORAJET® products and the continuing development of new applications, it is the responsibility of the purchaser to carefully evaluate the suitability and performance of the product for its intended use. Furthermore, the processing instructions issued by ORAFOL must be observed. The purchaser bears all risks arising from the use of these products. All information is subject to change without notice. ORAJET® is a registered trademark of ORAFOL Europe GmbH.