ORAJET® 3650

Digital Printing Film

Short description

Partially polymer PVC film, available in white with glossy or matt surface.

Front material

Partially polymer PVC film, 0.07 mm

Liner

One-sided siliconized kraft paper, 143 g/m²

Adhesive

Solvent-polyacrylate, permanent, Transparent, 0.026 mm

Technical properties

RESISTANCE

Durability	with vertical outdoor exposure, normal Central European climate	
	5 Year(s)	Applies for vertical outdoor weathering, central European normal climate; unprinted
Shelf Life	2 Year(s)	in original packaging, at 20 °C and 50% relative humidity
Maximum shrinkage	Maximum shrinkage along 0.4 mm	Bonded to steel | Average value, FINAT TM 14
Elongation at break	Minimum elongation at break along 130 % Minimum elongation at break across 150 %	DIN EN ISO 527
Tensile strength	Minimum tensile strength along 19 N/mm² Minimum tensile strength across 19 N/mm²	DIN EN ISO 527
Seawater resistance	no change	after 100h/35°C | adhered to aluminum, DIN EN ISO 9227
Temperature resistance	Minimum temperature -40 °C Maximum temperature 80 °C	Short-term exposure up to 110 °C |

ORAFOL Europe GmbH
Orafolstrasse 1
D-16515 Oranienburg
Germany

Tel: +49 (0)3301 864-0
graphic.solutions@orafol.de
www.orafol.com

ORAJET® 3650

Digital Printing Film

ADHESIVE PROPERTIES

Adhesive power	18 N/25 mm	after 24 h, on stainless steel | FINAT TM 1, average value

PROCESSING

Application temperature	Minimum temperature 10 °C

PRODUCT NOTE

After printing, the ink must be allowed to thoroughly dry, in order to avoid any issues when later combined with the laminate. Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of the selected lacquers and paints should be tested by the user, prior to the application of the material. Furthermore the application information published by ORAFOL must be considered.

IMPORTANT NOTES

All ORAJET® products are subject to careful quality control throughout the manufacturing process. It is guaranteed that the products are delivered in merchantable quality and free of manufacturing defects. The traceability of our goods in accordance with ISO 9001 is ensured by means of the roll number. The information published on ORAJET® products is based on research results that the company believes to be reliable, but does not constitute a guarantee. Because of the wide variety of uses of ORAJET® products and the continuing development of new applications, it is the responsibility of the purchaser to carefully evaluate the suitability and performance of the product for its intended use. Furthermore, the processing instructions issued by ORAFOL must be observed. The purchaser bears all risks arising from the use of these products. All information is subject to change without notice. ORAJET® is a registered trademark of ORAFOL Europe GmbH.

ORAFOL Europe GmbH
Orafolstrasse 1
D-16515 Oranienburg
Germany

Tel: +49 (0)3301 864-0
graphic.solutions@orafol.de
www.orafol.com