

Description

ORALITE® GP 027 is a flexible glass bead garment tape designed for heat application onto garments, e.g. professional high visibility rain wear. ORALITE® GP 027 exceeds the minimum reflectivity requirements of EN ISO 20471:2013.

Product Construction

ORALITE® GP 027 is composed of wide-angle, exposed retroreflective lenses bonded to a heat activated polyurethane adhesive. The adhesive is protected by a polyethylene liner and the reflective side is protected by a polyester liner.

Product Approvals

EN ISO 20471:2013 Separate Performance

Colour

ORALITE® GP 027 is available in silver (daytime appearance) with a white reflected colour.

Retroreflectivity

ORALITE® GP 027 exceeds the minimum reflectivity requirements of EN ISO 20471:2013, when tested at $e = 0^\circ$ or $e = 90^\circ$ in accordance with the procedures defined in EN ISO 20471. Minimum coefficients of retroreflection are shown in Table 1.

Machine Washing

ISO 6330:2012, Method 6N – 50 washes at 60° C.

Dry Cleaning

Certified in accordance with ISO 3175-2:2010
Normal Cycle – 25 cycles.

Application Instructions

ORALITE® GP 027 has a single layer construction with a heat activated polyurethane adhesive backing. The protective plastic liner must be removed from the adhesive side prior to heat application. Please contact ORAFOL for full application instructions.

Shelf Life

The product must be used within one year from the shipment date. All rolls including partially used rolls should be stored in original packaging, tightly wound. Store in a clean and dry area, away from direct sunlight. Store at 20° C and 50% relative humidity.

Table 1 - Retroreflectivity

Observation Angle	Entrance Angle ($\beta_1, \beta_2=0$)			
	5°	20°	30°	40°
0,20° (12')	450	290	180	65
0,33° (20')	250	200	170	60
1,00° (1°)	25	15	12	10
1,50° (1°30')	10	7	5	4

All values have units of cd/lux/m².

Care Symbols



IMPORTANT NOTE

All ORAFOL products are subject to careful quality control throughout the entire manufacturing process, and it is ensured that they are of merchantable quality and free from manufacturing defects. The information published is based on our analyses and studies and does not constitute any warranted properties or any agreement as to quality. Due to the diverse possibilities of use of ORAFOL products and the constant development of new applications, the buyer should carefully consider the suitability and performance of the product for the respective purpose; it bears all risks associated with such use. No warranty is given for purposes other than those listed in the Technical Data Sheet or for applications that are not processed in accordance with ORAFOL's processing instructions.

The durability of the end product depends upon a variety of factors, including but not limited to substrate selection and preparation, compliance with the recommended application guidelines, geographical area, exposure conditions and maintenance of the ORAFOL material and of the end product. Product defects caused by the substrate or improper surface preparation do not lie within ORAFOL's sphere of responsibility.

When using ORAFOL products, the pertinent national regulations are to be observed. ORAFOL recommends that you obtain the current stipulations from your local authority and ensure that the product meets these requirements. Please contact ORAFOL for further information.

ORALITE® is a registered trademark of ORAFOL Europe GmbH.