

Product Description

SolaTuf® AC2 Impact Modified Acrylic Film is less modified than SolaTuf® AC1 and SolaTuf® AC6, which equates to a higher modulus and higher tensile strength. SolaTuf® has transparency that far exceeds polycarbonate film.

Technical Data

Physical

Specific Gravity	ASTM D-792	g / cm ³	1,17
Water Absorption 24 Hours	ASTM D-570	%	0,30
Rockwell Hardness	ASTM D-785	M Skala	62

Optical

Refractive Index @ 25°C	ASTM D-542	N _b	1,49
Light Transmission	ASTM D-1003	%	92,0
Haze	ASTM D-1003	%	<4.0

Mechanical

Tensile Strength, Break	ASTM D-638	MPa	47
Tensile Elongation, Break	ASTM D-638	%	35
Tensile Modulus of Elasticity	ASTM D-638	MPa	2.580
Flexural Strength	ASTM D-790	MPa	75
Flexural Modulus	ASTM D-790	MPa	2.270
Notched Izod Impact @ 23°C	ASTM D-256	J / m an Kerbe	37

Thermal

Deflection Temperature under Flexural Load @ 1.8 MPa - Annealed	ASTM D-648	°C	85
Coefficient of Thermal Expansion	ASTM D-696	cm / cm / °C	8 x 10 ⁻⁵
Vicat Softening Temperature - Unannealed	ASTM D-1525	°C	99
Glass Transition Temperature, T _g	ASTM D-3418	°C	104
Maximum Continuous Service Temperature	---	°C	68 - 79

IMPORTANT NOTICE

All RowTec® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning RowTec® products is based upon research, which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of RowTec® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice.

RowTec® is a registered trademark of Rowland Technologies Inc. - An Orafol company.

